

# **SPF12V7.2-ST** Standard Type Battery

# LITHIUM IRON PHOSPHATE BATTERY

ELECTRICAL PERFORMANCE			
Nominal Voltage	12.8 V		
Nominal Capacity	7.2 Ah		
Capacity @ 1.5A	300 min		
Energy	92 Wh		
Resistance	≤50 mΩ @ 50% SOC		
Self Discharge	<3% / Month		
Cells	IFR26650EC		

CHARGE PERFORMANCE			
Recommended Charge Current	1.5 A		
Maximum Charge Current	7.2 A		
Recommended Charge Voltage	14.6 V		
BMS Charge Cut-Off Voltage	<15.6 V (3.9V/Cell)		
Reconnect Voltage	>14.4 V (3.6V/Cell)		
Balancing Voltage	<14.4 V (3.6V/Cell)		
Maximum Batteries in Series	6		

DISCHARGE PERFORMANCE			
Maximum Continuous Discharge Current	15 A		
Peak Discharge Current	30 A (3s)		
BMS Discharge Cut-Off Current	45 A ±5 A (31 ms)		
Recommended Low Voltage Disconnect	11.0 V (2.75V/Cell)		
BMS Discharge Cut-Off Voltage	>8.0 V (2s) (2.0V/Cell)		
Reconnect Voltage	>10.0 V (2.5V/Cell)		
Short Circuit Protection	250 ~ 500 μs		





MECHANICAL PERFORMANCE			
Dimension (L x W x H)	151 x 65 x 99 mm 5.9 x 2.6 x 3.9"		
Approx. Weight	2.0 lbs (0.9 kg)		
Terminal Type	F2		
Case Material	ABS		
Enclosure Protection	IP65		


TEMPERATURE PERFORMANCE		
Discharge Temperature	-4 ~ 140 °F (-20 ~ 60 °C)	
Charge Temperature	arge Temperature 32 ~ 113 °F (0 ~ 45 °C)	
Storage Temperature	23 ~ 95 °F (-5 ~ 35 °C)	
BMS High Temperature Cut-Off	149 °F (65 °C)	
Reconnect Temperature	131 °F (55 °C)	

COMPLIANCE	
Certifications	CE (battery) UN38.3 (battery) UL1642 & IEC62133 (cells)
Shipping Classification	UN 3480, CLASS 9

#### **OUTLINE DIMENSION**







L mm(")	W mm(")	H mm(")	HT mm(")
151 (5.9)	65 (2.6)	85 (3.3)	99 (3.9)

Performance may vary depending on application. All specifications are subject to change without prior notice to the user. This data is for evaluation purposes only. No guarantee is intended or implied by this data. For clarification and updated information, please contact us.










#### **Standard Type Battery SPF12V7.2-ST**


#### PERFORMANCE CHARACTERISTICS







Discharge characteristic at different rate at room temperature



#### **FEATURES & BENEFITS**

#### High cycle life

>2000 cycles @80% DoD for effectively lower total cost of ownership.



#### Longer service life

Low maintenance batteries with stable chemistry.



# **Built in circuit protection**

Battery Management System (BMS) is incorporated against abuse.



## **Better storage**

up to 6 months thanks to its extremely low self discharge (LSD) rate and no risk of sulphation.



## Quickly recharge

Save time and increase productivity with less down time thanks to superior charge/discharge efficiency.



#### Extreme heat tolerance

Suitable for use in a wider range of applications where ambient temperature is unusually high: up to +60°C.



#### Lightweight

Lithium batteries provide more Wh/Kg while also being up to 1/3 the weight of its SLA equivalent.

#### **APPLICATIONS**

Lithium Iron Phosphate can be used in most applications that use Lead Acid, GEL or AGM type batteries. Suitable applications include:

- Fishing sonar
- Electrical devices
- Toys
- Emergency light
- Digital camera
- Remote Monitoring
- Switching applications and more

### **CAUTIONS**

- Do NOT short circuit, crush or disassemble.
- Do NOT heat or incinerate.
- Do NOT immerse in any liquid.
- Store at 30~50% SOC. Recharging every 3 months is recommended. The storage area should be clean, cool, dry and ventilated.

Performance may vary depending on application. All specifications are subject to change without prior notice to the user. This data is for evaluation purposes only. No guarantee is intended or implied by this data. For clarification and updated information, please contact us.





